

UNIVERSITAS
LAMBUNG MANGKURAT

Dewi Puspitasari <dewipuspitasari@ulm.ac.id>

SUBMIT PAPER DENTINO

3 messages

Dewi Puspitasari <dewipuspitasari@ulm.ac.id>
To: dentino.fkg@ulm.ac.id

Thu, Aug 11, 2022 at 1:17 PM

Kepada Yth. Dentino,

Dengan ini saya mohon ijin mengirimkan dan submit paper untuk dapat diterima diterbitkan di dentino. Atas perhatiannya saya ucapkan terima kasih.

Best Regards,
Dewi Puspitasari

 **DENTINO SEPTEMBER 2022.docx**
48K

dentino fkg <dentino.fkg@ulm.ac.id>
To: Dewi Puspitasari <dewipuspitasari@ulm.ac.id>

Mon, Aug 22, 2022 at 12:39 PM

Kepada YTH : Author

Mohon naskah direvisi sesuai arahan editor (review dg tulisan merah). Segera diperbaiki dan dikembalikan maksimal kamis 25 agust 2022

Regards,
Editor Jurnal Dentino
[Quoted text hidden]

 **Dewi FKG ULM Review1.docx**
60K

Dewi Puspitasari <dewipuspitasari@ulm.ac.id>
To: dentino fkg <dentino.fkg@ulm.ac.id>

Mon, Aug 22, 2022 at 1:29 PM

Kepada YTH. Editor Dentino,
Dengan ini kami kirimkan naskah yang telah direvisi.
Kami telah memperbaiki pada urutan abjad keyword dan juga penambahan pada referensi dentino pada no 12.
Terima kasih atas perhatiannya.

Regards,
Dewi Puspitasari
[Quoted text hidden]

 **Dewi FKG ULM Review1.docx**
48K

THE RELEASE OF FLUORIDE IONS OF BIOACTIVE RESIN IN THE SOLUTION OF LACTIC ACID AND ARTIFICIAL SALIVA

Dewi Puspitasari¹⁾, Nadya Fatimah Alzahrah²⁾, Indri Indah Tari²⁾, Diana Wibowo³⁾, Rahmad Arifin⁴⁾, Renie Kumala Dewi⁵⁾, Sherli Diana⁶⁾

¹⁾ Department of Dental Material, Faculty of Dentistry, University of Lambung Mangkurat, Banjarmasin

²⁾ Dentistry Study Program, Faculty of Dentistry, University of Lambung Mangkurat, Banjarmasin

³⁾ Department of Orthodontics, Faculty of Dentistry, University of Lambung Mangkurat, Banjarmasin

⁴⁾ Department of Prosthodontics, Faculty of Dentistry, University of Lambung Mangkurat, Banjarmasin

⁵⁾ Department of Pediatric Dentistry, Faculty of Dentistry, University of Lambung Mangkurat, Banjarmasin

⁶⁾ Department of Conservative Dentistry, Faculty of Dentistry, University of Lambung Mangkurat, Banjarmasin

ABSTRACT

Background: Bioactive resin can release fluoride ions when contact with oral environment. In the oral cavity, saliva and metabolic results of *Streptococcus mutans* namely lactic acid may affect the release of ions due to pH changes. **Purpose:** to analyze the release of fluoride ions of bioactive resin in the solution of lactic acid and artificial saliva. **Methods:** Forty-two specimens (diameter 15 mm x thickness 1 mm; n=7/group) fabricated with Activa™ Bioactive Restorative (Pulpdent). The specimen were randomized into six 6 groups which immersed in lactic acid, artificial saliva and distilled water for 1 and 7 days in the incubator at 37°C. The number of fluoride ion release was measured using pH Meter (Lutron-208). **Results:** Two Way Anova test and Post Hoc Bonferonni test show there are significant differences among all group for lactic acid 1 day (6.37 ± 0.74), artificial saliva 1 day (1.30 ± 0.48), distilled water 1 day (3.78 ± 0.97), lactic acid 7 days (22.9 ± 0.81), artificial saliva 7 days (19.00 ± 0.81), distilled water 7 days (21.60 ± 1.01) ppm. **Conclusion:** The fluoride ion release of bioactive resin which immersed in lactic acid solution was higher than in artificial saliva immersion.

Keywords: artificial saliva, bioactive resin, fluoride ion release, lactic acid, (urut abjad)

Correspondence: Dewi Puspitasari, Faculty of Dentistry, University of Lambung Mangkurat, Jalan Veteran No 12B, Banjarmasin, Indonesia, email: dewipuspitasari@ulm.ac.id

INTRODUCTION

Dental caries is a multifactorial disease of dental hard tissue that damages the structure of the enamel, dentin and cementum.¹ Caries process begins with the presence of continuous demineralization of tooth due to irreversible solubilization of the tooth mineral caused by acid proceeded by certain bacteria such as *Streptococcus mutans*. Dominant acid produced by *Streptococcus mutans* is lactic acid.^{2,3,4} Caries management to preserve and restore natural tooth structure are determined by the type of lesion, restorative material applications are usually to be the preferred approaches.^{3,4} One of the most common causes of restoration failure is secondary caries.⁵ Secondary caries are caries lesions lied at the marginal of restoration or caries tied to restoration or sealant.⁶

As the times progress, the use of resin-based restorative materials is significantly increased.^{7,8} Composite resins are globally used

due to good esthetics with high strength. In 2013 bioactive composite resin was introduced as a bioactive restorative material with the "smart behaviour".^{7,9} The bioactivity of these materials can be attributed to its ability to release ions and provide ionic exchange with saliva and tooth structure thereby remineralization could be promoted surrounding tooth structure. Bioactive composite resins consist of matrix and filler from that differed from conventional composite resins. Filler of this resin contains reactive glass filler (21.8 wt%), inorganic filler (56 wt%), rubberized resin, amorphous silica (6.7%), sodium fluoride (0.75%) and water. Matrix is a mixture of diurethane and methacrylate modified with 44.6% polyacrylic acid.¹⁰ Bioactive composite resins has water absorption and solubility properties due to the presence of amorphous silica.⁸ Mechanically, bioactive composite resins are stronger than conventional composite resins due to their rubberized content, ionic-resin which contains less water therefore it is more resistant to shock.¹¹

Bioactive composite resins have chemical properties that are able to release and recharging phosphate, calcium and fluoride.⁸

Bioactive composite resins release more phosphate, fluoride and calcium ions than glass ionomers. Phosphate, fluoride and calcium ions, stimulate remineralization and apatite formation.^{8,10} Fluoride has remineralization activity that helps strengthen tooth tissue structure and inhibits demineralization by combining fluoride with calcium to form fluoroapatite.^{8,12,13} This bond is more stable and more resistant to acids due to the bond structure formed is more complex.¹³

The ability of bioactive resin to take and release fluoride is dependent on factors such as fluoride content and also changes of oral pH.¹⁴ Oral environment pH including salivary pH may turn to acid condition due to the metabolism of *Streptococcus mutans*.¹⁵ This state may affect the properties of bioactive resin including the release of fluoride ions.^{15,16} Conventional composite resin-based restorative materials have no ability to release fluoride ions for tooth remineralization as do as GIC, but conventional GIC can not conform the strength of conventional composite resin. Therefore, the use of bioactive resins is expected to represent both of restorative materials in terms of strength and ion releasing properties.¹⁴ Bioactive resin released fluoride ions without a burst effect on the first day but the level of fluoride ion release remained relatively constant for a week (7 days).¹⁶ There is still limited study of the release of fluoride ions from the first day to the seventh day especially in the lactic acid immersion and artificial saliva. The purpose of the study is to analyze the release of fluoride ions of bioactive resin in the solution of lactic acid and artificial saliva.

MATERIALS AND METHODS

The study was approved by the ethical clearance test published by the Faculty of Dentistry, Lambung Mangkurat University No. 012/KEPKG-FKGULM/EC/II/2021. The samples were prepared using bioactive resin (Activa™ Bioactive Restorative, Pulpdent) with 15 mm in diameter and 1 mm in thickness of plastic mold in a total of forty-two specimens.

The bioactive resin was mixed and extruded from syringe through a spiral gun and applied to the mold. The top of the mould was covered by celluloid strip followed by glass slide and gently pressed. Specimens were light cured with a LED Light Curing Unit with an output of 800 mW/cm² for 20s on the top of mould surfaces and the tip touching the glass,

subsequently stored in incubator for 24 h at 37°C. All specimens were immersed based on the group treatment as follows: (1) immersion on lactic acid solution for 1 day, (2) artificial saliva for 1 day, (3) distilled water for 1 day, (4) lactic acid solution for 7 days, (5) artificial saliva for 7 days, (6) distilled water for 7 days; all immersion media are treated with pH measurement (lactic acid solution pH 5.2, artificial saliva pH 6.7 and distilled water pH 7), replaced every day during the study process and stored in incubator with the temperature of 37°C.

The release amount of ion release measurement was conducted by using pH Meter (Lutron-208). The bioactive resins specimens were ground using a mortar and paste until fine particles were obtained and then diluted using 10 ml of distilled water and 10 ml of sodium fluoride buffer. The electrode was immersed into the sample solution for 3 minutes using a pH meter (Lutron-208). The calculation of the amount of fluoride release was carried out by subtracting the baseline bioactive composite resin by the number of the fluoride calculated using a pH meter (Lutron-208).

Data analysis was carried out with a two-way test ANOVA with a confidence level of 95% ($\alpha = 0.05$) and continued using the Bonferroni Post Hoc test to determine the value of significance.

RESULTS

The mean values of the amount of fluoride ions release in the bioactive resin are summarized in table 1.

The mean and standard deviation of the number of fluoride ion release of bioactive resin.

Immersion media and time	Mean± SD (µg)
Lactic acid 1 d	6.37 ± 0.74 ^A
Artificial saliva 1 d	1.30 ± 0.48 ^B
Distilled water 1 d	3.78 ± 0.97 ^C
Lactic acid 7 d	22.90 ± 0.81 ^D
Artificial saliva 7 d	19.00 ± 0.81 ^E
Distilled water 7 d	21.60 ± 1.01 ^F

Two Way Annova test

*Different superscript letters indicate significant differences.

The table 1 showed that the highest mean amount of fluoride ion release was in the group of bioactive resin specimens immersed in lactic acid solution for 7 days, while the group with the lowest mean amount of fluoride release was the group of artificial saliva immersion for 1 day.

The results of Two-Way Annova test showed that the significance value of the immersion media group was $p = 0.000$ ($p < 0.05$), which means that there was a significant difference in the number of

fluoride ion release of bioactive resin immersed in lactic acid, artificial saliva and distilled water. The significance value of the immersion time group was $p=0.000$ ($p<0.05$), which means that there was a significant difference in the amount of fluoride ion release in the bioactive resin that was immersed for 1 and 7 days. The significance value of the immersion media and time was $p=0.138$ ($p>0.05$), which means there was no interaction between the immersion media and time. Bonferroni Post Hoc test show that there are significant differences among all group.

DISCUSSION

The capability of composite resin-based bioactive materials to release fluoride ions may attributed to the remineralization of the surrounding tooth.¹⁶ The released fluoride which taken up by the enamel and dentin, making the tooth structure more resistant to acids by a combination of decreasing solubility and impairing the activity of cariogenic bacteria. Fluoride ion dynamics provide an advantage for tooth that have a high susceptibility to caries.⁷

In the oral cavity, many factors may affect the amount of fluoride ion release in bioactive composite resins, one of which is the pH value of oral cavity and also saliva. In the present study, to represent the condition of oral cavity we conducted the treatment of bioactive resin in the immersion of lactic acid and artificial saliva. Lactic acid has the most acidic degree of acidity (4.2) followed by artificial saliva (6.7) and aquadest (7.0). The lower the pH value, the more the reservoir releases fluoride ions. Our study is in line with Abdallah (2019) that bioactive resins may released more fluoride ions in acidic pH than neutral pH.¹³ This is due to an acidic state contain more H^+ ions, result in the release of the chemical structure of the bioactive composite resin and stimulating the release of fluoride ions.^{14,17,18} Meanwhile, artificial saliva and aquadest have a neutral pH which does not ionize more to produce H^+ ions, resulting in the release of fluoride ions. The more acidic pH may alter the properties of materials by releasing more ions and result in the loss of material. This loss may reduce the life and durability of the materials. The loss of material may attributed to the higher amount of resin matrix leads to increase water sorption and softening the specimen ion release from filler particles can result in separating of matrix and filler, and also by micro-cracks formation in interface of filler-matrix interface pH.^{7,18}

Based on the results of study that has been carried out, the least amount of fluoride ion release was found in the bioactive composite resin immersed in artificial saliva for one day, although the pH value of artificial saliva was lower than that of distilled water. This possibility may occurred due to the

difference in viscosity between artificial saliva and distilled water. The specimens were immersed in distilled water to prevent any influence of minerals or organic molecules which might be presented in the solutions or artificial saliva.¹³ The presence of dissolved substances Na_2HPO_4 , $KSCN$, $NaCl$, KH_2PO_4 , KCl and $NaHCO_3$ contained in artificial saliva may causes the particle density to be greater and the viscosity to be higher.^{16,19} Meanwhile, distilled water is pure H_2O which has a smaller density and has a lower viscosity. High viscosity can make it difficult for artificial saliva to reach the filler in the bioactive composite resin, therefore the amount of fluoride ion release is less. The solute in artificial saliva is also a mineral salt with a normal pH that does not produce H^+ and OH^- ions due to an imperfect ionization process, the low H^+ content result in the ions released from artificial saliva were less.²⁰

Another factor that may cause the bioactive composite resin immersed in artificial saliva to release less fluoride ions when compared to distilled water is the presence of bioactive glass in the bioactive composite resin. The fluoride ion in the bioactive composite resin is found in the filler. The resin contains bioactive glass consisting of SiO_2 , CaO , Na_2O and P_2O_5 . Therefore, when water diffused and contact with the bioactive glass, a reaction occurs for the formation of hydroxyapatite (HA). Acid conditions and the presence of moisture due to the diffusion of water (H_2O) into the matrix of resin causes the breakdown of H_2O into H^+ and OH^- , then the silicon dioxide bond ($Si-O-Si$) is attacked by hydroxyl ions. The surface of the bioactive glass exposed to water results in the exchange of sodium and calcium ions with hydrogen ions from solution, forming $Si-OH$ groups and forming a layer rich in silica which undergoes polymerization, binding calcium ions and phosphate ions in the form of Amorphous Calcium Phosphate (ACP), which then crystallized into HA.²¹ If HA can bind to fluoride ions, fluoroapatite can be formed which can be a better remineralizing agent than HA. In order for the formation of HA and fluoroapatite can be conducted, the structure of the bioactive composite resin must be able to allow the diffusion of water to reach the bioactive glass and fluoride ions released from the structure of the bioactive composite resin.²²

Immersion the composite resin in lactic acid media, artificial saliva and aquadest for one day and seven days showed no interaction with the amount of fluoride ion release. Based on the statistical analysis test of Two Way Anova on the 1st and 7th day of immersion the amount of fluoride ion release of the bioactive composite resin showed the same results, namely lactic acid which was the highest followed by distilled water and the lowest was artificial saliva.

According to Francois (2020) study, bioactive composite resins in contact with an aqueous environment will release fluoride ions, calcium ions and phosphate ions.¹⁴ The release of fluoride ions can also occur when bioactive composite resins are exposed to saliva and solutions with critical pH.⁷ The use of immersion media also has an effect to the amount of fluoride ion released. The study conducted by Eriwati (2020) showed that the immersion of bioactive resins in a solution of critical pH (4.5) and normal pH (7.0) released more fluoride ions at critical pH.²³ The more acidic the environment around the bioactive composite resin, the more a lot of fluoride ions are released. The immersion time also has an effect on the amount of fluoride ion release. The longer the immersion time for the bioactive composite resin, the more fluoride will be released. In line with Ruengrungsom's study on day 4, more fluoride ions were released than on day 1.¹⁶ Ibrahim also stated that restoration materials based on composite resin released more fluoride ions on day 7 than day 1.²⁴ However, the result study was applied to immersion of bioactive resins for 1-7 days according to the present study. Within the limitations of this study, the following conclusions can be drawn is the fluoride ion release in the group of bioactive resin specimens immersed in lactic acid solution was higher than artificial saliva immersion.

ACKNOWLEDGEMENTS

We gratefully acknowledge the support of University of Lambung Mangkurat for research funding sources of Lecturer's Obligatory Program for Research 2022

REFERENCES (wajib ada referensi dentino)

- Butera A, Maioran C, Morandini A, Simonini M, Morittu S, Trombini J, *et al.* Evaluation of Children Caries Risk Factors: A Narrative Review of Nutritional Aspects, Oral Hygiene Habits, and Bacterial Alterations. *Children*. 2022;9 (2): 1-14.
- Ismail AI, Pitts NB, Tellez M, Banerjee A, Deery C, Douglas G, *et al.* The International Caries Classification and Management System (ICCMS™) An Example of a Caries Management Pathway. *BMC Oral Health*. 2015;15 (Suppl 1): S9.
- Baker JL, Faustofferi RC, Quivey RG. Acid-adaptive mechanisms of *Streptococcus mutans*-the more we know, the more we don't. *Molecular Oral Microbiology*. 2016; 32(2): 107-117.
- Cheng L, Zhang L, Yue L, Ling J, Fan M, Yang D, *et al.* Expert Consensus on Dental Caries Management. *International Journal of Oral Science*. 2022. 14 (17): 1-8.
- Haghoo R, Mehran M, Ahmadvand M, *et al.* Remineralization Effect of Eggshell versus Nano hydroxyapatite on Caries-like Lesions in Permanent Teeth (In Vitro). *Journal of International Oral Health*. 2016; 8(4): 435-439.
- Nedeljkovic I, De Munck J, Vanloy A, Declerck D, Lambrechts P, Peumans M, *et al.* Secondary Caries: Prevalence, Characteristics, and Approach. *Clin Oral Investig*. 2020. 24 (2): 683-691.
- Kasraei S, Haghi S, Farzad A, Malek M, Nejadkarimi S. Comparative of Flexural Strength, Hardness, and Fluoride Release of Two Bioactive Restorative Materials Restorative Materials with RMGI and Composite Resin. *Brazilian Journal of Oral Science*. 2022; 21 (2): 1-16.
- Alrahlah A. Diametral Tensile Strength, Flexural Strength, And Surface Microhardness of Bioactive Bulk Fill Restorative. *The Journal of Contemporary Dental Practice*. 2018. 19 (1): 13-19.
- Rosalinda D, Puspitasari D, Nahzi MYI. The Effect of Air-Drying Time on Bonding (Self Etch) With Ethanol as A Solvent to The Shear Bond Strength of Bioactive Composite Resin. *Dentino Jurnal Kedokteran Gigi*. 2021;6(1):65-71
- Kaushik M, Yadav M. Marginal Microleakage Properties of Activa Bioactive Restorative and Nanohybrid Composite Resin Using Two Different Adhesives in Non-Carious Cervical Lesions- An In Vitro Study. *Journal of the West African College of Surgeons*. 2017; 7 (2): 1-14.
- Bhadra D, Shah NC, Rao AS, Dedania MS, Bajpai N. A 1-year comparative evaluation of clinical performance of nanohybrid composite with Activa™ bioactive composite in Class II carious lesion: A randomized control study. *J Conserv Dent*. 2019; 22(1): 92-96.
- Puspitasari D, Tajjalina N, Wibowo D, Wardhana AS. The Effect of Lactic Acid and Artificial Saliva Solution Immersion to The Release of Calcium Ions on Bioactive Resin. *Dentino Jurnal Kedokteran Gigi*. 2021;6(2):190-194.
- Abdallah A, Elshehawey T, Ibrahim H. Fluoride Release and Recharge Behavior of Bioactive Glass Ionomer Cements

- using Ion Chromatography. *Egyptian Dental Journal*, 2019; 65(1): 399-406
14. Francois P, Fouquet V, Attal JP, Dursun E. Commercially Available Ion Fluor Releasing Restorative Materials: A Review and a Proposal for Classification. *Materials*. 2020; 13 (3): 3-28.
 15. Liao Y, Brandt BW, Li J, Crielaard W, Van Loveren C, Deng DM. Fluoride resistance in *Streptococcus mutans*: a mini review. *J Oral Microbiol*. 2017 Jul 6;9(1)
 16. Ruengrungsom, C, Burrow M, Parashos P, Palamara JEA. Evaluation of F, Ca, and P release and microhardness of eleven ion-leaching restorative materials and the recharge efficacy using a new Ca/P containing fluoride varnish. *Journal of Dentistry*. 2020; 102 (22): 1-23.
 17. Kafalia RK, Firdausy MD, Nurhapsari A. Pengaruh Jus Jeruk dan Minuman Berkarbonasi Terhadap Kekerasan Permukaan Resin Komposit. *ODONTO Dental Journal*. 2017; 4 (1): 38-43.
 18. Adiba SH, Effendy R, Zubaidah N. Fluoride Varnish Effect on Dental Erosion Immersed with Carbonated Beverages. *Journal of International Dental and Medical Research*. 2018; 11 (1): 299-302.
 19. Langen EN, Rumampuk JF, Leman MA. Pengaruh Saliva Buatan dan belimbing Wuluh (*Averrhoa bilimbi* L.) Terhadap Kekerasan Resin Komposit Nano Hybrid. *PHARMACON Jurnal Ilmiah Farmasi*. 2017; 6 (1): 2302-2493.
 20. Par M, Gubler A, Attin T, Tarle Z, Tarle A, Taubock TT. Ion Release and Hydroxyapatite Precipitation of Resin Composites Functionalized with Two Types of Bioactive Glass. *J Dent*. 2022; 1 (18): 10390.
 21. Fatwati K, Puspitasari D, Apriasari ML. Effect of *Musa Acuminata* and *Ocimum Basilicum* Mixed Extract on Bioactive Resin's Fluoride Release. *DENTINO Jurnal Kedokteran Gigi*. 2020; 5 (1): 94-97.
 22. Rahayu YC. Peran Agen Remineralisasi Pada Lesi Karies Dini. *Stomatogantic (J. K. G Unej)*. 2013; 10(1): 25-30.
 23. Eriwati YK, Dhiaulfikri M, Herda E. Effect of Salivary pH on Water Absorptions and Solubility of Enhanced Resin-Modified Glass Ionomer. *Journal of Dentistry Indonesia*. 2020; 27 (3): 64-69.
 24. Ibrahim SA, Mohamed AA, Kamar AA, Bakry NS. Comparison Between Nano-Hybrid Composite and Resin Reinforced Glass Ionomer in Fluoride Release and Recharge Capacity (In Vitro Study). *Alexandria Dental Journal*. 2020; 45 (3): 114-119.